

## Technical Data Sheet

# MAESTRO MOSAIC PARQUET ADHESIVE

*one-component water-based adhesive*



<b>product description:</b>	MAESTRO MOSAIC PARQUET ADHESIVE is based on aqueous dispersion of polyvinyl acetate fillers and additives for gluing mosaic and classic parquet on concrete, cement, wood and similar absorbent substrates.
<b>area of application:</b>	It is used for gluing classic and mosaic parquet on concrete, wooden and similar surfaces.
<b>assortment:</b>	MAESTRO MOSAIC PARQUET ADHESIVE
<b>consumption:</b>	0.8 – 1.2 kg/m <sup>2</sup> for one layer
<b>density:</b>	1.30 kg/l (EN ISO 2811-1)
<b>viscosity:</b>	18000 – 20000 mPa·s (EN ISO 2555 at 20°C)
<b>pH:</b>	6 – 7
<b>non-volatile-matter content:</b>	63 – 65 % (EN ISO 3251)
<b>working conditions:</b>	The temperature of the air, material and substrate during processing must be higher than +10 °C, less than +25 °C, and relative humidity less than 75 %. Do not work at temperatures lower than +10 °C!
<b>application:</b>	The surface must be dry, flat, smooth and well cleaned of grease and dust. The adhesive should be applied evenly on the substrate with a notched trowel in a layer thickness of about 1 mm. After finishing the work, the tool should be washed well with water immediately!  For any additional info, please contact a Chromos-Svjetlost technical advisor.
<b>coating drying:</b>	Dry: 24 h (20 °C at 65 % relative humidity)  Full strength after 48 hours
<b>overcoating interval:</b>	The adhesive binds after a few hours, but further processing is recommended only after 24-48 hours, under optimal conditions (18-22 °C, RH up to 65%).
<b>transport and storage:</b>	Store in a dry and well-ventilated place out of direct sunlight at a temperature of +5 to +25 °C. Protect it from freezing.
<b>shelf life:</b>	In unopened packaging 12 months from the date of production.
<b>note:</b>	Protect from freezing!  It meets the strictest criteria for the protection of human health and the environment.  Parquet glue is not flammable!
<b>certificates:</b>	For each production batch, the relevant documentation is submitted.
<b>product/packaging disposal:</b>	Empty the packaging completely. Dispose of in accordance with valid regulations to an authorized waste collector.
<b>quality control:</b>	Product quality characteristics are determined by internal production specifications, as well as European and Croatian standards. The product is under the constant supervision of factory quality control Chromos-Svjetlost d.o.o.
<b>disclaimers:</b>	Before using the product, please check its quality. In case of any major deviations from the declared properties of the product, stop the use and contact the manufacturer; otherwise any subsequent complaints will not be accepted.  Technical data are the result of our technical and experimental knowledge, and are provided with the intention of achieving optimal results in working with CHROMOS-

## Technical Data Sheet

# MAESTRO MOSAIC PARQUET ADHESIVE

*one-component water-based adhesive*



SVJETLOST products. The data does not contain a legal or secondary obligation of the manufacturer nor does it release the user from the obligation to check the suitability of the product for particular purpose. Due to the use of natural raw materials in our products, minor deviations from certain values are possible for individual deliveries. Contact our Technical service before use on substrates not listed in the accompanying documentation. The manufacturer reserves the right to make any subsequent changes to the Technical Data Sheet. Only the latest edition is valid. Updated Technical Data Sheets can be found on the website [www.chromos-svjetlost.hr](http://www.chromos-svjetlost.hr) or can be requested from the manufacturer via the contact e-mail address below. Contact our Technical service for more detailed information. Be sure to read the safety labels on the product packaging before use. Safety Data Sheet is available on request.

October, 2021.

Quality and Environmental management systems certified in accordance with TÜV NORD Croatia;  
Certificate No: 44 100 134668 / 44 104 134668

