

## Technical Data Sheet

# MAESTRO PUTTYING LIQUID

*fast-drying liquid for filling joints of parquet*



<b>product description:</b>	Fast-drying liquid based on modified binders in organic solvents.
<b>field of application:</b>	It is used to fill joints, minor damages and unevenness in the parquet surface treatment system.
<b>assortment:</b>	MAESTRO PUTTYING LIQUID
<b>thinner:</b>	Maestro puttying liquid is not diluted. To wash tools, use Maestro equipment cleaner.
<b>coverage:</b>	8 – 15 m <sup>2</sup> /l depending on the size of the joints
<b>consumption:</b>	0.06 – 0.125 l / m <sup>2</sup> depending on the size of the joints
<b>density:</b>	0.92 – 0.96 kg/l (EN ISO 2811-1)
<b>viscosity:</b>	70 – 110 s (EN ISO 2431, DIN 4 at 20 °C)
<b>non-volatile-matter content:</b>	20 % (EN ISO 3251)
<b>volatile organic compound (VOC) content:</b>	A(h), 750 g/l; max: 749 g/l (EN ISO 11890-1)
<b>working conditions:</b>	The temperature of the air, material and substrate during processing must be higher than +10 °C, less than +25 °C, and relative humidity less than 75 %.
<b>application:</b>	The liquid must be stirred before use. On previously sanded parquet with sandpaper no. 60 – 80, a liquid to which wood dust has been added is applied. The liquid is applied with a trowel in 1-2 layers depending on the size of the joints. To fill the joints, you should use wood dust from the parquet being processed so that the shade of the filled surface does not deviate from the shade of the parquet.  The dried liquid layer must be well sanded with sandpaper no. 80-100. For any additional info, please contact a Chromos-Svjetlost technical advisor.
<b>drying time:</b>	Up to 45 minutes under normal conditions (working temperature 18-22 °C, relative air humidity up to 65 %, parquet humidity between 8 and 10 %)
<b>overcoating interval:</b>	After 1 hour, a second layer of Maestro liquid (if necessary) or a layer of Maestro impregnation can be applied to the previously sanded first layer (intercoat interval applies to normal working conditions).
<b>transport and storage:</b>	Store in a dry and well-ventilated place out of direct sunlight at a temperature of +5 to +25 °C.
<b>shelf life:</b>	In unopened packaging 12 months from the date of production.
<b>certificates:</b>	For each production batch, the relevant documentation is submitted.
<b>product/package disposal:</b>	Empty the packaging completely. Dispose of in accordance with valid regulations to an authorized waste collector.
<b>quality control:</b>	Product quality characteristics are determined by internal production specifications, as well as European and Croatian standards. The product is under the constant supervision of factory quality control Chromos-Svjetlost d.o.o.
<b>disclaimers:</b>	Before using the product, please check its quality. In case of any major deviations from the declared properties of the product, stop the use and contact the manufacturer; otherwise any subsequent complaints will not be accepted.  Technical data are the result of our technical and experimental knowledge, and are provided with the intention of achieving optimal results in working with CHROMOS- SVJETLOST products. The data does not contain a legal or secondary obligation of the manufacturer nor

## Technical Data Sheet

# MAESTRO PUTTYING LIQUID

*fast-drying liquid for filling joints of parquet*



does it release the user from the obligation to check the suitability of the product for particular purpose. Due to the use of natural raw materials in our products, minor deviations from certain values are possible for individual deliveries. Contact our Technical service before use on substrates not listed in the accompanying documentation. The manufacturer reserves the right to make any subsequent changes to the Technical Data Sheet. Only the latest edition is valid. Updated Technical Data Sheets can be found on the website [www.chromos-svjetlost.hr](http://www.chromos-svjetlost.hr) or can be requested from the manufacturer via the contact e-mail address below. Contact our Technical service for more detailed information. Be sure to read the safety labels on the product packaging before use. Safety Data Sheet is available on request.

October, 2021.

Quality and Environmental management systems certified in accordance with TÜV NORD Croatia;  
Certificate No: 44 100 134668 / 44 104 134668

